

**ABLESTIK 55**

April 2015

**PRODUCT DESCRIPTION**

ABLESTIK 55 provides the following product characteristics:

|                           |   |
|---------------------------|---|
| <b>Technology</b>         | Epoxy   |
| <b>Appearance (Resin)</b> | White liquid  |
| <b>Product Benefits</b>   | <ul style="list-style-type: none"><li>• General purpose</li><li>• Low viscosity</li><li>• Can be used with a variety of catalysts</li><li>• Unfilled</li><li>• Good wetting</li><li>• Good chemical, solvent and water resistance</li></ul> |
| <b>Application</b>        | Assembly  |
| <b>Substrates</b>         | Glass, ceramic, metals, plastics and wood   |

ABLESTIK 55 adhesive applications include electronic component assembly, staking, tamperproofing of adjustment and calibration screws, anchoring inserts, end filling, hermetic sealing, and others.

ABLESTIK 55 can be used with CATALYST 9 or CATALYST 23LV.

**CATALYST DESCRIPTION**

CAT 9 provides the following product characteristics:

|   |   |
|---|---|
| <b>Product Benefits</b>                         | <ul style="list-style-type: none"><li>• General purpose</li><li>• Good chemical resistance</li><li>• Good physical strength</li></ul> |
| <b>Cure</b>                                     | Room temperature cure   |
| <b>Mix Ratio, by weight - Material:Catalyst</b> | 100 : 13.5  |
| <b>Mix Ratio, by Volume - Material:Catalyst</b> | 100 : 15.5  |
| <b>Operating Temperature</b>                    | -40 to 130°C  |

CAT 23LV provides the following product characteristics:

|   |   |
|---|---|
| <b>Product Benefits</b>                         | <ul style="list-style-type: none"><li>• Low colour</li><li>• Low viscosity</li><li>• Long pot life</li><li>• Excellent thermal shock and impact resistance</li><li>• Excellent low temperature properties</li><li>• Excellent adhesion to glass</li></ul> |
| <b>Cure</b>                                     | Room temperature cure   |
| <b>Mix Ratio, by weight - Material:Catalyst</b> | 100 : 28  |
| <b>Mix Ratio, by Volume - Material:Catalyst</b> | 100 : 32  |
| <b>Operating Temperature</b>                    | -65 to 105°C  |

**TYPICAL UNCURED PROPERTIES****ABLESTIK 55**

|  |        |
|--|--------|
| Brookfield Viscosity , mPa·s (cP)                  | 16,000 |
| Density, g/cm <sup>3</sup>                         | 1.18   |
| Shelf Life @ 25°C (from date of manufacture), days | 365    |

**CAT 9**

|                               |    |
|-------------------------------|----|
| Viscosity @ 25 °C, mPa·s (cP) | 90 |
| Flash Point - See SDS         |    |

**CAT 23LV**

|                               |    |
|-------------------------------|----|
| Viscosity @ 25 °C, mPa·s (cP) | 25 |
| Flash Point - See SDS         |    |

**TYPICAL UNCURED PROPERTIES AS MIXED****ABLESTIK 55 with CAT 9**

|                                   |       |
|-----------------------------------|-------|
| Density, g/cm <sup>3</sup>        | 1.14  |
| Brookfield Viscosity ,            | 8,000 |
| Work Life @ 25 °C, 100 g, minutes | 45    |

**ABLESTIK 55 with CAT 23LV**

|                                   |       |
|-----------------------------------|-------|
| Density, g/cm <sup>3</sup>        | 1.12  |
| Brookfield Viscosity , mPa·s (cP) | 3,300 |
| Work Life @ 25 °C, 100 g, minutes | 60    |

**TYPICAL CURING PERFORMANCE****Cure Schedule****ABLESTIK 55 with CAT 9**

16 to 24 hours @ 25°C or  
4 to 6 hours @ 45°C or  
1 to 2 hours @ 65°C

**ABLESTIK 55 with CAT 23LV**

24 hours @ 25°C or  
4 to 6 hours @ 45°C or  
2 to 4 hours @ 65°C

For optimum performance, follow the initial cure with a post cure of 2 to 4 hours at the highest expected use temperature.

Alternate cure schedules may also be possible.  
Contact your Henkel representative for further information.

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.



**TYPICAL PROPERTIES OF CURED MATERIAL****ABLESTIK 55 with CAT 9****Physical Properties**

Coefficient of Thermal Expansion , ppm/°C 59

**Electrical Properties**

Dielectric Strength , kV/mm 17

Dielectric Constant / Dissipation Factor:

@ 1 MHz 3.3/0.02

Volume Resistivity, ohms-cm:

@ 25 °C  $1 \times 10^{15}$ @ 93 °C  $1 \times 10^{11}$ **Outgassing Properties**

Outgassing , ASTM E 595, %:

TML 0.45

CVCN 0.02

**GENERAL INFORMATION**

**For safe handling information on this product, consult the Safety Data Sheet, (SDS).**

**DIRECTIONS FOR USE**

1. Complete cleaning of the substrates should be performed to remove contamination such as oxide layers, dust, moisture, salt and oils which can cause poor adhesion or corrosion in a bonded part.
2. Some separation of components is common during shipping and storage. For this reason, it is recommended that the contents of the shipping container be gently but thoroughly mixed prior to use.
3. Power mixing is preferred to ensure a homogeneous product.
4. Accurately weigh resin and hardener into a clean container in the one of the recommended ratios. Weighing apparatus having an accuracy in proportion to the amounts being weighed should be used.
5. Blend components by hand, using a kneading motion, for 2 to 3 minutes and scrape the bottom and sides of the mixing container frequently to produce a uniform mixture.
6. Scrape the bottom and sides of the mixing container frequently to produce a uniform mixture.
7. If possible, power mix for an additional 2 to 3 minutes. Avoid high mixing speeds. This can entrap excessive amounts of air. It can also cause overheating of the mixture, resulting in reduced working life.
8. Apply adhesive to all surfaces to be bonded and join together.
9. In most applications only contact pressure is required.

**STORAGE:**

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage : 25 °C**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

**Not for product specifications**

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.



## Disclaimer

### Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

### Trademark usage

All trademarks in this document are trademarks and/or registered trademarks of Henkel in the US and elsewhere.

### Reference 1

Supplied by:  
[www.hitek-ltd.co.uk](http://www.hitek-ltd.co.uk)  
 +44 (0)1724 851678



**HITEK**  
 ELECTRONIC MATERIALS LTD