



STYCAST 2 CN

Optically Clear, Repairable, Silicone Encapsulant

Key Feature:	Benefit:
• Optical clarity	• Facilitates visual inspection of protected components
• High temperature properties	• Assemblies can withstand severe temperature conditions
• Repairability	• Defective components replaced easily

Product Description:

STYCAST 2 CN is a water white, RTV silicone potting compound. It has excellent high temperature properties, is very flexible, and can be readily repaired.

Applications:

STYCAST 2 CN is designed for potting applications which require identification, repair, or replacement of defective components

Instructions For Use:

Thoroughly read the information concerning health and safety contained in this bulletin before using. Observe all precautionary statements that appear on the product label and/or contained in individual Material Safety Data Sheets (MSDS).

To ensure the long term performance of the potted or encapsulated electrical / electronic assembly, complete cleaning of components and substrates should be performed to remove contamination such as dust, moisture, salt, and oils which can cause electrical failure, poor adhesion or corrosion in an embedded part.

This RTV silicone product is based on condensation cure chemistry and will cure in contact with most materials without cure inhibition. This product is not recommended for use in closed molds or sealed molds which could prevent its exposure to moisture or the escape of reaction by-products required to complete the cure. In addition, catalysts used to cure this product may cause corrosion of copper and other sensitive metals.

Properties of Material As Supplied:

Property	Test Method	Unit	Value
Chemical Type			Silicone
Appearance Visual			Clear liquid
Density AST	M-D-792	g/cm ³	0.99
Brookfield Viscosity ASTM-D-2393	100 rpm # 5	Pa.s cP	1.7 1,700

Accurately weigh the liquid RTV silicone and catalyst into a clean container in the recommended ratio. To facilitate the addition of catalyst, the use of a medicine dropper which has been previously calibrated to determine the number of drops per gram is recommended. Working life and cure time are shortened as the amount of catalyst is increased. Low catalyst concentrations are recommended for applications requiring thick sections or use at temperatures in excess of 125°C.

Blend components by hand, using a kneading motion, for 2-3 minutes. Scrape the bottom and sides of the mixing container frequently to produce a uniform mixture. If possible, power mix for an additional 2-3 minutes. Avoid high mixing speeds which could entrap excessive amounts of air or cause overheating of the mixture resulting in reduced working life.

To ensure a void-free embedment, vacuum deairing should be used to remove any entrapped air introduced during the mixing operation. Vacuum deair mixture at 1-5 mm mercury. The foam will rise several times the liquid height and then subside. Continue vacuum deairing until most of the bubbling has ceased. This usually requires 3-10 minutes.

In general, silicone materials exhibit outstanding release properties and will not adhere to most substrates. If adhesion is required, apply a thin, uniform coating of PRIMER S 11 to the desired clean, dry substrates. Allow the PRIMER S 11 to dry for 30-60 minutes at room temperature before applying this silicone material.

Pour mixture into cavity or mold. Gentle warming of the mold or assembly reduces the viscosity. This improves the flow of the material into the unit having intricate shapes or tightly packed coils or components. Further vacuum deairing in the mold may be required for critical applications.

STYCAST 2 CN can be repaired easily. The encapsulating material may be cut from around the defective part, and the part replaced. The hole is then refilled with resin and allowed to cure at room temperature. The cure may be accelerated by exposure to temperatures up to 65°C.

Curing agent	Catalyst 50-2
Description	Standard condensation cure catalyst, yields slightly better adhesion and high temperature performance. Also slightly faster curing.
Type of cure	Room
Viscosity	Pa.s cP
	0.085 85

Properties of Material As Mixed:

Property	Test Method	Unit	Value
			Catalyst 50-2
Mix Ratio-Catalyst per 100 parts of STYCAST 2 CN		By Weight	0.3 to 0.5
Working Life (100 g @ 25°C)	ERF 13-70	minutes	60
Density AST	M-D-792	g/cm ³	0.99
Brookfield Viscosity	ASTM-D-2393	Pa.s cP	1.7 1,700

Cure Schedule:

Cure at any one of the recommended cure schedules. Where use at temperatures above 125°C is anticipated, a post cure schedule of 1-2 hours at 25-30°C increments up to the highest expected use temperature is recommended to properly condition the silicone rubber.

Temperature	Cure Time (hrs)
°C	Catalyst 50-2
25	16-24
65	4-6

Properties of Material After Application:

Property	Test Method	Unit	Value
			Catalyst 50-2
Hardness AST	M-D-2240	Shore A	22
Temperature Range of Use		°C	-65 to +200

Storage and Handling:

The shelf life of STYCAST 2 CN is 6 months at 25°C. For best results, store in original, tightly covered containers. Storage in cool, clean and dry areas is recommended. Usable shelf life may vary depending on method of application and storage conditions.

Attention Specification Writers:

The values contained herein are considered typical properties only and are not intended to be used as specification limits. For assistance in preparing specifications, please contact HITEK

Health and Safety:

The STYCAST 2 CN, like most industrial compounds, possesses the ability to cause skin and eye irritation upon contact. Handling this product at elevated temperatures may also generate vapours irritating to the respiratory system.

Good industrial hygiene and safety practices should be followed when handling this product. Proper eye protection and appropriate chemical resistant clothing should be worn to minimize direct contact. Consult the Material Safety Data Sheet (MSDS) for detailed recommendations on the use of engineering controls and personal protective equipment.

This information is only a brief summary of the available safety and health data. Thoroughly review the MSDS for more complete information before using this product.

"In the event this product is intended by you for use in implantation in the human body, you are hereby advised that Henkel Corporation has not performed clinical testing of these materials for implantation in the human body nor has Henkel Corporation sought, nor received, approval from the FDA for the use of these material in implantation in the human body. It is YOUR responsibility, as a manufacturer of any such device, to ensure that all materials and processes relating to the manufacture of any medical device fully comply with all applicable federal, state and local laws, rules, regulations and requirements as well as any such laws, rules, regulations, directives or other orders of any foreign country where such product is sold. If you have not undertaken the necessary investigations to ensure compliance you are advised NOT TO USE this product in the manufacture of any device which is to be implanted in the human body. No representative of ours has any authority to change the foregoing provisions."

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Supplied by: www.hitek-ltd.co.uk +44 (0)1724 851678		HITEK ELECTRONIC MATERIALS LTD
--	---	--

Americas
+1.888.943.6535

Europe
+32.1457.5611

Asia
+86.21.3898.4800

For the most direct access to local sales and technical support visit: www.henkel.com/electronics