

Technical Data Sheet




UK Distributors
HITEK Electronic Materials Ltd.
15 Wentworth Road
Scunthorpe
DN17 2AX
+44 (0) 1724 851678
www.hitek-ltd.co.uk

DD-10218


Description

- Flexible, loaded silicone magnetic absorber.
- Tuned for mode suppression in an enclosed cavity, signal isolation, and surface current attenuation.
- Available with pressure sensitive adhesive (PSA).
- Standard sheet size:
 - 12" x 12" (30.48 cm x 30.48 cm).
 - Custom sheet sizes available upon request.
- Can be water-jet or die cut for custom configurations.
- Halogen free, RoHS and REACH compliant.

Properties	Test Method	Value
Durometer	ASTM D2240	85 Shore A
Tensile Strength	ASTM D638	347 psi
Elongation	ASTM D638	188%
Surface Resistivity	ASTM D257	> 11 GΩ/□
Max Operating Temperature	--	375°F (190°C)
Flammability Rating	--	UL94 V-0
Standard Sheet Thickness	--	0.200" (5.08 mm) Other thicknesses available upon request.
Color	--	Gray



Thickness tolerance on DD = 0.127mm (0.005")



Note: the information provided is accurate at time of publication.

It is the responsibility of the end-user to confirm compliance to their application. All test data is typical.

