

# STYCAST 1090 SI CAT 9

May 2019

## PRODUCT DESCRIPTION

LOCTITE STYCAST 1090 SI CAT 9 provides the following product characteristics:

<b>Technology</b>	Epoxy
<b>Appearance (Resin)</b>	Black
<b>Components</b>	Two components - requires mixing
<b>Mix Ratio, (by weight)</b>	100 : 11
<b>Resin : Hardener</b>	
<b>Product Benefits</b>	<ul style="list-style-type: none"> <li>• Low density</li> <li>• Low dielectric constant</li> <li>• High compressive strength</li> <li>• Two component</li> </ul>
<b>Cure</b>	Room temperature cure
<b>Application</b>	Encapsulation
<b>Operating Temperature</b>	-70 to 125 °C

LOCTITE STYCAST 1090 SI CAT 9 encapsulant is recommended for applications where high compressive stress is applied to encapsulated circuitry - as in deep ocean work. This product will have a minimum effect on electronic circuit operation and shows negligible deformation and water absorption.

LOCTITE STYCAST 1090 SI can be used with a variety of catalysts. For more information on mixed properties when used with other available catalysts, please contact your local technical service representative for assistance and recommendations.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

### Part A Properties LOCTITE STYCAST 1090 SI

Viscosity @ 25 °C, mPa·s (cP)	30,000 to 50,000
Specific Gravity	0.6 to 0.7
Shelf Life @ 18 to 25°C, months	12
Flash Point - See SDS	

### Mixed Properties

Mixed Viscosity, mPa·s (cP)	5,000 to 10,000
Specific Gravity	0.7 to 0.8
Pot Life @ 25 °C, minutes	30
Flash Point - See SDS	

## TYPICAL CURING PERFORMANCE

### Cure Schedule

4 to 24 hours @ 25°C

### Post Cure

4 hours @ 60 to 100°C may be required to achieve the best reliability results

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

## TYPICAL PROPERTIES OF CURED MATERIAL

### Physical Properties :

Coefficient of Thermal Expansion ASTM D 3386, K <sup>-1</sup>	58×10 <sup>-6</sup>
Glass Transition Temperature ISO 11359-2, °C	50 to 60
Thermal Conductivity, W/(m·K)	0.13 to 0.18
Shore Hardness, ISO 868, Durometer D	≥75
Tensile Strength, ISO 527-2	N/mm <sup>2</sup> 20 (psi) (2,900)
Compressive Strength, ISO 604	N/mm <sup>2</sup> 65 (psi) (9,425)
Compressive Modulus, ISO 604	N/mm <sup>2</sup> 2,000 (psi) (290,000)

### Electrical Properties:

Volume Resistivity, IEC 60093, Ω·cm	≥1×10 <sup>13</sup>
Dielectric Constant / Dissipation Factor, IEC 60250:	
60Hz	2.9 / 0.025
1 kHz	2.7 / 0.02
1 MHz	2.3 / 0.03

## DIRECTIONS FOR USE

1. Accurately weigh resin and hardener into a clean container in the recommended ratio.
2. Mix thoroughly in the can in which it is received.
3. Liquid diluents can be supplied to lower viscosity at some sacrifice in properties.
4. Pour mixture into cavity or mold.
5. Mold release 122 S will prevent adhesion. (Evacuation may be necessary to remove trapped air and is recommended for high quality embedments. It is often convenient to remove the trapped air from the resin prior to pouring into mold, and then again evacuate briefly when the mold is filled).
6. Allow to stand at room temperature for about 4 hours. Removal from the mold prior to that time is possible if the casting is hard.
7. The filler will tend to float during storage. Premixing before use is required.

## STORAGE:

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage : 18 to 25 °C**

## GENERAL INFORMATION

**For safe handling information on this product, consult the Safety Data Sheet, (SDS).**

Certain resins and hardeners are prone to crystallization. If crystallization does occur, warm the contents of the shipping container to 50 to 60°C until all crystals have dissolved. Be sure the shipping container is loosely covered during the warming stage to prevent any pressure build-up. Allow contents to cool to room temperature before continuing.

#### Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

#### Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$   
 $\text{kV/mm} \times 25.4 = \text{V/mil}$   
 $\text{mm} / 25.4 = \text{inches}$   
 $\text{N} \times 0.225 = \text{lb/F}$   
 $\text{N/mm} \times 5.71 = \text{lb/in}$   
 $\text{psi} \times 145 = \text{N/mm}^2$   
 $\text{MPa} = \text{N/mm}^2$   
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$   
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$   
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$   
 $\text{mPa}\cdot\text{s} = \text{cP}$

#### Disclaimer

##### Note

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel, is therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

#### Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 3

<p>Supplied by:</p> <p><a href="http://www.hitek-ltd.co.uk">www.hitek-ltd.co.uk</a></p> <p>+44 (0)1724 851678</p>	 <p><b>HITEK</b> ELECTRONIC MATERIALS LTD</p>
---	--

Americas  
+1.888.943.6535

Europe  
+32.1457.5611

Asia  
+86.21.2891.8000

**For the most direct access to local sales and technical support visit: [www.hitek-ltd.co.uk](http://www.hitek-ltd.co.uk)**