
## shielde<u>x</u>



## Shieldex<sup>®</sup> Wrapped Yarn - dyed red

200471011026 Preliminary

Core Material 100/26 2 ply PA 6.6

Wrapped Material 44 /10 PA 6.0

Metal Plated 99.9 % Pure Silver

Yarn count silverized  $295 \, dtex \pm 10 \, \%$ 

Electrical Resistivity  $\leq 1.5 \text{ k}\Omega/\text{m}$ 

Yield  $34.000 \, \text{m/kg} \pm 5 \, \%$ 

Tenacity  $40 \pm 5 \text{ cN}$ Elongation / Break  $37 \% \pm 5$ 

Make Up On cones 230 mm 3° 30

Packaging Average 450 g net yarn per cone

Storage and Handling According to our care and handling instructions

Compliance and Certification DIN EN ISO 9001:2015, REACH, RoHS

Alterations Reserved 04.11.21/01 — The above information has been compiled from our manufacturer area according to the latest state of development and application technology. Since application and further processing are beyond our control, no liability of the producer can be derived from the contents of the data sheet. All deviant or transcending data sheet information must be confirmed in written form by the manufacturer. Our general terms and conditions apply in all cases. All previous data sheets are invalid with the publication of this data sheet. Please note our handling and storage instructions as well accessible at www.shieldex.de.

