



CorShield® VpCI®-146 Paper Recyclable, Biodegradable, Compostable, Patent Pending

DESCRIPTION

CorShield[®] VpCl[®]-146 with Eco-Bio[®] Technology is the premium corrosion inhibiting paper in the industry. It relies on Cortec's patented biodegradable and compostable Vapor phase Corrosion Inhibiting Technology, which has revolutionized the way metals are protected in an enclosed package.

Both sides of CorShield® VpCl®-146 paper offer effective protection to ferrous and nonferrous metals, eliminating the need to stock a variety of papers for different metal types. Simply wrap items in the paper and fold the edges together, taping as needed to hold paper in place. The VpCl® coating on the paper vaporizes, reaching all metal surfaces within the package to provide complete corrosion protection with a very thin, very effective VpCl® layer that does not alter product appearance or require removal before further finishing or use.

CorShield[®] VpCl[®]-146 paper is madefrom 100% recycled content paper and is fully recyclable/ repulpable. It is biodegradable and compostable It contains 92% USDA certified biobased content and is a qualified product under the mandatory federal purchasing initiative of the USDA BioPreferred[®] Program.*

PACKAGING & STORAGE

To ensure best product performance, store in original packaging, indoors, and out of direct sunlight at 40-100 °F (4-38 °C).

HIGH PERFORMANCE VPCI® PACKAGING



FEATURES

- Made with 100% recycled content paper
- Contains 92% USDA certified biobased content
- Compostable per ASTM D6868
- Contains no nitrites, phosphates, silicones, chromates, or other heavy metals
- Fully recyclable, repulpable
- Commercial equivalent to MIL PRF-3420
- Protective layer does not need to be removed prior to further surface finishing or coating application
- Tested by Zagreb, Croatia-Department of Health, for use on food articles
- Does not influence physical properties of most sensitive electrical components, including conductivity and resistance
- Patent pending

BENEFITS

- One product for all ferrous and non-ferrous metals
- Combines corrosion protection and packaging into one step
- Effective protection on both sides of paper eliminates packaging guesswork
- Protects dry or oiled metals during storage, transit, and overseas shipment
- Effective against aggressive environments including humidity, SO₂, H₂S, and galvanic corrosion from dissimilar metals

METALS PROTECTED

- Carbon Steel
- Stainless Steel
- Galvanized Steel
 - Cast Iron
- Aluminum Alloys
- Copper
- Brass (≤30% Zn)
- Solder

Shelf life: 2 years

*For more information about the BioPreferred® Program, please visit: https://www.biopreferred.gov.

TYPICAL PROPERTIES

Property	Unit	Value	
Basis Weight	lbs/3000 ft² (g/m²)	35±1.5 (57±2.5)	
Caliper	Mils (µm)	4.0±0.2 (100±5)	
Tear Strength	gms	CD*	50±5
		MD*	70±10
Tensile Strength	lb _r /in (N/mm)	23 (4)	
Burst Strength (Mullen Test)	Psi (kPa)	20 (138)	

*CD = Cross Direction *MD = Machine Direction

SIZES

Standard Sizes, 35 lb/3000 ft² (57 g/m²)				
Roll Stock	Sheets	Perforated Rolls		
12" x 600' (60.1 cm x 182.9 m) 18" x 600' (45.7 cm x 182.9 m) 24" x 600' (601 cm x 182.9 m) 36" x 600' (91.4 cm x 182.9 m) 48" x 600' (121.9 cm x 182.9 m) 36" x 1200' (91.4 cm x 365.76 m)	4" x 8" (10.2 cm x 20.3 cm) 6" x 6" (15.2 cm x 15.2 cm) 9" x 9" (22.9 cm x 22.9 cm) 10" x 10" (25.4 cm x 25.4 cm) 12" x 12" (30.5 cm x 30.5 cm) 16" x 16" (40.6 cm x 40.6 cm) 18" x 18" (45.7 cm x 45.7 cm) 24" x 24" (61 cm x 61 cm) 36" x 36" (91.4 cm x 91.4 cm)	12" x 12" x 600' (30.5 cm x 30.5 cm x 182.9 m)		
A wide variety of stock and custom sizes and constructions are also available upon request in 30 lb (49 g/m ²), 35 lb (57 g/m ²), 40 lb (65 g/m ²), and 60 lb (98 g/m ²) paper.				

ACC VACION - 166 VARIOR PHASES MULTI-METAL PROTECTS ACC VACION - 166 VARIOR PHASES MULTI-METAL PROTECTS CONSTRUCTION - CONSTRUCTION - CONSTRUCTION CONSTRUCTION - CONSTR

Day 1

After 4 Weeks



After 10 Weeks

Compostability testing in accordance with ASTM Standard D6868



LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec® Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec® Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec® Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec® Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec® Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products. BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec® Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC® CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.

Revised: 06.27.22. Supersedes: 07/27/21. ©Cortec Corporation 2002-2022 of Cortec® Corporation. All Rights Reserved. Copying and/or manipulation of these materials in any form without the written authorization of Cortec® Corporation is strictly prohibited. 2022, ©Cortec® Corp. ISO accreditation applies to Cortec's processes only.