VpCI®-350 Multimetal Coating for Folding/Corrugated Box industries

DESCRIPTION

VpCI-350 is a multimetal Vapor Phase Corrosion Inhibitor coating for the folding box and corrugated box industries. VpCI-350 produces a thin, non-penetrating coating for chipboard and cardboard that has exceptional shelf-life without the corrosion problems that have been associated with this type of packaging in the past.

The constructions that are produced with this coating are expected to be useful to many companies that now rely on heavy oils, greases, and/or additional paper wrappings to provide corrosion protection in a box or package. VpCl-350 provides multimetal protection to many metals including steel, galvanized steel, copper, brass, silver, solder and aluminum.

APPLICATION

VpCI-350 is a water-based product that is supplied as a two-part mixture (VpCI-350 A and VpCI-350 B). The solutions are mixed at a 1:1 ratio at the time of coating and can be applied directly to the liner or inside surface with most common roll coaters such as gravure, flexo, air-knife, reverse-roll, or Michaelmans coaters. The unused mixed coating solution should be discarded after 30 days. Drying of the coating is usually accomplished in a warm air oven or with IR bulbs.

Coating weights of 3-5 lb per ream (4.9-8.2 g/m²) are suggested. In cases when a highly reactive metal is packaged, or long-term protection for use in warm and humid climates is needed, a heavier coating weight is recommended.

PHYSICAL PROPERTIES

<u>VpCI-350 A</u>

Appearance Hazy off-white to pale yellow

liquid

Non-volatile Content 15-20%

pH 8.1-8.5 (Neat)

Density 8.6-8.7lb/gal (1.03-1.04 kg/l)

VpCI-350 B

Appearance Blue to green liquid

Non-volatile Content 43-53%

Density 8.7-8.8 lb/gal (1.04-1.05 kg/l)

PACKAGING AND STORAGE

VpCl-350 is available in 5 gallon (19 liter) pails, 55 gallon (208 liter) drums, liquid totes, and bulk.





FOR INDUSTRIAL USE ONLY KEEP OUT OF REACH OF CHILDREN **KEEP CONTAINER TIGHTLY CLOSED** NOT FOR INTERNAL CONSUMPTION CONSULT SAFETY DATA SHEET FOR MORE INFORMATION

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec* Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Corlec® Corporation warrants Corlec® products will be free from defects when shipped to customer. Corlec® Corpora tion's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obstain replacement product under this warranty, the customer must notify Corlec's Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec® Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to

use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE,

AND USER ASSUMES ALL RISK AND LIABILITY WHAT SOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec® Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC* CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



4119 White Bear Parkway, St. Paul, MN 55110 USA Phone (651) 429-1100, Fax (651) 429-1122 Toll Free (800) 4-CORTEC, E-mail info@cortecvci.com http://www.cortecvci.com

Distributed by:







printed on recycled paper 10% post consumer
Revised 5/16/12. ©Cortec Corporation 2000-2012. All rights reserved. Supersedes: 1/30/06.
© 2012, Cortec Corporation. All Rights Reserved. Copying of these materials in any form without the written authorization of Cortec Corporation is strictly prohibited. ISO accreditation applies to Cortec's